

**NOTES:**

1. SPACING FOR CONCRETE RESTRAINING ANCHORS SHALL BE AS SHOWN ON THE PLANS.
2. THE PORTION OF THE ANCHOR IN UNDISTURBED GROUND SHALL BE POURED UNFORMED.
3. CONCRETE SHALL BE 3000 PSI.
4. CONCRETE ANCHOR TO BE POURED AROUND BELL OF PIPE WHERE APPLICABLE.
5. USE ON SLOPES EQUAL TO OR GREATER THAN 20%.
6. PIPE SHALL BE DUCTILE IRON PIPE.



THE CITY OF LYNCHBURG

CONCRETE RESTRAINING
ANCHOR

USE WITH THE CITY OF LYNCHBURG STANDARD SPECIFICATIONS ONLY

SCALE:
NOT TO SCALE

REVISION DATE:
11-06-2006

DETAIL #
27.21

SHEET #:
1 OF 1